



Certificate of Analysis

BITUMEN 20/30

No	Characteristic	Value	Test Method
1	Penetration @ 25°C, 100g, (dmm); 5sec	20-30	EN 1426
2	Softening Point (Ring & Ball)	65-53	EN 1427
3	Kinematic Viscosity @ 135°C	530 min	EN 12595
4	Solubility %	99 min	EN 12592
5	Flash Point (Cleveland Open) (°C)	240 min	EN 22592
Performance after RTFOT Method Test to EN 12607-1:			
1	Change in mass, (%wt)	0.5 max	-
2	Retained Penetration 25°C, 100g, 5s (% of original)	≥ 55 min	-
3	Increase in Softening Point (°C)	≤ 8 max	-
4	Softening Point After Hardening (°C)	57 min	-