



Certificate of Analysis

BITUMEN CSS-1h

No	Property	Min	Max	Test Method
1	Viscosity, Say bolt Furol at 25°C,SFS	20	100	ASTM D244
2	Storage stability Test, 24-h, %	-	1	ASTM D6930
3	Particle Charge Test	Positive		ASTM D244
4	Sieve Test, %	-	0.1	ASTM D6933
5	Cement Mixing Test,%	-	2	ASTM 6935
Distillation				
1	Residue %	59	-	ASTM D244
Test On Residue From Distillation				
1	Penetration, 25°C(77°F), 100g, 5s	40	90	ASTM D5
2	Ductility, 25°C(77°F), 5 cm/min, cm	40	-	ASTM D113
3	Solubility in trichloroethylene, %	97.5	-	ASTM D2042